SAVANNAH BLACK



RECOMMENDED APPLICATIONS			TECHNICAL SPECIFICATIONS			
FLOORS & WALLS	SHOWER FLOORS & WALLS	EXTERIOR PAVING FREEZE THAW STABLE	COMPRESSIVE STRENGTH	TENSILE STRENGTH	WATER ABSORPTION	BULK DENSITY
YES	YES	YES	2370 kg/cm ²	275 kg/cm ²	0.02%	2930 kg/m ³
	ST				MA	RY OF ORIGIN italy ATERIAL granite
• STONE IS A NATURA PICTURES FOR EVEL			S AND RANGE		RANGE	

SP